

**iTraff™ Rapide  
Acrylic Waterborne Traffic Paint  
Red**

**Introduction**

**iTraff™ Rapide** Traffic Paints are very fast drying acrylic waterborne paints for use in marking parking lots, airports, and roads. These paints may be applied ambient airless or conventional, or may be heated for even faster dry. This paint dry to no pickup in less than 20 minutes when properly applied at ambient conditions. It is user friendly, high solids, traffic marking paint and offers all of the benefits of a water reducible paint, and quickly dries to a no track condition in 20 minutes or less making it an ideal striping product for roadways, airfields and even parking lots.

This waterborne acrylic paint has excellent chemical and dirt resistant which provides exceptional adhesion to concrete and asphalt surfaces.

**Some key Product Features are as follows:**

- Non Flammable
- High visibility
- Ready to use
- Glass beads can be added for marking reflective markings
- Longer glass beads retention
- Good wear and weathering resistance
- Suitable for direct application on asphalt and concrete roads

**Recommended Uses**

For marking parking lots, curbs, and other areas when very fast dry times are not critical, and water based or low VOC coatings are required or desired.

- Airport Markings
- Parking lots
- City and Municipalities Roads
- Kerb Marking
- Cross Walks
- Temporary Markings

**Recommended Spreading Rate:**

Wet (Approx.) 375 microns  
 Dry (Approx.) 225 microns  
 ~Coverage 1.4-1.6 m<sup>2</sup>/Kg  
*Coverage will vary depending on Surface type and surface condition*

**Drying Schedule @ 375 microns wet @ 25°C, 50% RH**

**To touch** : 10-20 minutes  
**No traffic pickup after** : 45 minutes  
*Drying time is temperature, humidity, and film thickness dependent*

**Specification**

Tests	Unit	Typical Values
Color	-	Red
Gloss	-	Matt
Volume Solids	%	Min 60
Recommended WFT / Coat	microns	100 - 1000
<b>Theoretical Coverage</b>		
@ 300 mic (11.8 mils)	Sq. mt/Kg	2.0
@ 375 mic (14.8 mils)	Sq. mt/Kg	1.6
<b>Drying Time at 30°C</b>		
Surface dry	minutes	10 - 20
Recommended drop on Glass Beads	-	As per BS 3262 / FAA
Viscosity @ 30 °C	KU	80 - 105
White Reflectance (Y value)	-	Min 84
Yellow Reflectance (Y value)	-	Min 50
Hiding at 127 microns wet	-	Min 92
Weight % Pigment Solids	%	60 ± 2

**Directions For Use**

- Ensure that the road surface is clean, free from dust, oil and grease, loose sand, aggregate and chipping/peeling existing striping.
- For thorough removal of dust from the surface; wire brushing & water washing is recommended
- Any curing compounds used on new concrete must be mechanically scraped away/worn away prior to striping.
- Heavy deposits of earlier paint or thermoplastic should be removed
- When striping on freshly sealed surfaces use caution as some sealers can affect the curing and adhesion of traffic paint.
- For complete drying and minimum dirt retention when striping parking lots, the lots should be closed to traffic for two hours minimum after painting.
- The surface should be thoroughly dry and free from moisture
- Surface temperature must be at least 3°C above dew point but not above 60°C
- Do not paint at temperatures below 10°C or at relative humidity over 85%
- Under cold and humid conditions the paint would require longer drying time

**iTraff™ Rapide  
Acrylic Waterborne Traffic Paint  
Red**

**Mixing Conditions**

If settling is observed in the drum, loosen the settled material with the help of a hand stirrer followed by a power driven stirrer for quick homogenous mixing.

**Application Conditions**

- The product is formulated for air / airless spray application only. The equipment selected i.e. all the tanks, spray gun, piping, valves, strainers etc. should be grade 304 stainless steel or higher. Confirm the compatibility of the selected equipment with the machine supplier prior to commencement of operations
- While thinning is normally not recommended, if required thin sparingly with water. When spraying, prevent air from entering the material system
- **iTraff™ Rapide** is suitable for adding regular or high Index glass beads for retroreflectivity
- Typically, 350 gms / sqm glass beads are required. The glass beads must be immediately dropped at appropriate pressure for optimum penetration in the stripe thereby ensuring long term retroreflectivity. The glass beads of the specified diameter should only be used. Smaller diameter glass beads would imply the need for a lower WFT thereby reducing the effective service life of the coating
- The equipment must be cleaned immediately after use. Tanks, lines and gun should be thoroughly cleaned using clean water. Any paint that has dried and doesn't readily wash with water can be removed using ketonic solvents
- **ITS Coatings** recommends application using **Graco® Airless Spray Equipments** for best results

**Clean Up Instructions**

Clean spill and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

**Storage & Waste Disposal**

- A minimum shelf life of 12 months when stored in a cool, dry and covered place
- For professional use only.
- Keep water based paints from freezing.
- Keep away from children.
- Proper agitation and mixing of paint is imperative to ensure proper spray consistency, application results and performance.
- Make sure lids are properly closed and resealed properly to avoid any spillage during prep work or transportation.
- Strictly comply with all local and federal regulations during storage, application and disposal of paints.

**Packaging**

- 20 Kgs Plastic Pails

**Disclaimer**

The information above is believed to be accurate and represents the best information currently available to us. However, we make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and we assume no liability resulting from its use, handling and or from contact. Users should make their own investigations to determine the suitability of the information for their particular purposes. In no way ITS Coatings Pvt. Ltd be liable for any claims, losses, or damages of any third party or for lost profits or any special, indirect, incidental, consequential or exemplary damage, howsoever arising, even ITS Coatings Pvt. Ltd has been advised of the possibility of such damages

Reference No: ITSC/P-00059	Issue Date: July 8, 2014	Prepared By: Prachi Pimparkar	Date: 11/10/2019
Revision No: 04	Revision Date: October 11, 2019	Approved By: Deepali Nikam	Date: 11/10/2019

